

served to prove that embedding along a curved enclosed fiber path was viable, thus enabling a suite of mechanisms unique to AM processes.

Some features of the proposed process do place limitations on the types of mechanisms that can be created. Due to the layer-by-layer nature of the 3D Printing process, fibers can only be embedded within a single plane. No part of the fiber can protrude above the surface of the part that was being fabricated when the build process is resumed. If any protrusions are allowed to form, the print head will catch upon them as the build process is resumed and the part, fiber, or print heads will be damaged. This places a limit on the complexity of mechanisms that can be created with this process.

Furthermore, the current method of removing support material from the channel prior to embedding is a manual process and depends greatly on the skill of the machine operator as well as the tools used. For optimal results to be achieved, the channel should be fabricated with no support material within. However, the capability of doing this is hindered by the Objet Studio software, which automatically inserts support material in areas that would be required for standard prototype fabrication.

The method used to secure the filament within fixation channels was a combination of a press fit within the channel as well as using a small quantity of manually applied photopolymer resin as an adhesive. This method, however, proved to be only marginally more effective than the press fit alone. Thus it was observed that the bond strength of the photopolymer on the monofilament fiber was poor. For assemblies requiring higher tension forces, an alternative adhesive would be required to provide adequate fixation.

5. CLOSURE AND FUTURE WORK

The authors present in this paper a method for creating actuated assemblies using the Objet PolyJet 3DP process. Taking advantage of the technology's ability to create parts with both rigid and flexible materials, the authors propose a technique wherein fibers are embedded into the assembly to serve as ligaments that can be actuated.

The process begins with the design of both the part and the channel into which the fiber will be embedded, with careful consideration given to the required clearances of the fiber and the channel. The second step in the process is to pause the build process at the proper layer (with the aid of a pause indicator built from a unique material) and clear the support material from the channels. The fiber is then embedded into the part and secured by depositing liquid photopolymer resin and exposing the area to UV light at the proper wavelength to cure the material. Finally, the build is resumed and allowed to finish normally.

This process has been validated with two successful case studies that both achieved actuation with living hinge joints as well as revolute joints. However, we recognize that there are limitations in the current method. One limitation is that this method is only viable for a planar fiber path, and also requires that multiple fibers embedded into the same part lie in parallel planes. A second limitation is that a skilled operator is required to not only pause the build, but to clean the channels, manually embed the fiber, and bond the fiber to the part.

Possible further work would be to assess the viability of shape memory alloy (SMA) as an implantable actuator. The use of SMA may be limited due to the poor heat resistance of the photopolymer material used in the Objet PolyJet process. Furthermore at this point, the embedding of an object larger than a filament of 0.015 inch width has not been attempted. Further work into embedding of larger objects will serve to define the boundaries of this approach. The current ability to embed fibers allows for basic circuits to be formed by substituting conductive material for the fiber used previously; however, embedding of electrical components that would be needed to complete the circuit is an as of yet unexplored part of this technology. The embedding of electrical components and circuits, as well as piezoelectric material, combined with the multi-material capability of the process, could lead to the additive manufacture of energy harvesting devices.

6. REFERENCES

- Alam, M., C. Mavroidis, N. Langrana, and P. Bidaud, 1999, "Mechanism Design using Rapid Prototyping," *Proceedings of the 10th World Congress on the Theory of Machines and Mechanisms*, Oulu, Finland, 3, pp. 930-938.
- Bailey, S. A., J. G. Cham, and M.R. Cutkosky, "Comparing the Locomotion Dynamics of a Cockroach and a Shape Deposition Manufacturing Biomimetic Hexapod," Department of Integrative Biology, University of California at Berkeley.

- Bailey, S. A., J. G. Cham, M. R. Cutkosky, and R.J. Full, 2000, "Biomimetic Robotic Mechanisms via shape Deposition Manufacturing," *Robotics Research: the Ninth International Symposium*, John Hollerbach and Dan Koditschek (Eds), Springer-Verlag, London.
- Bailey, S. and J. Clark, "Sprawlita." 25 January 2000. Stanford University Biomemetics. <<http://www-cdr.stanford.edu/biomimetics/documents/sprawlita/sprawlita.html>>.
- Beck, J.E., F. B. Prinz, D. P. Siewiorek and L.E. Weiss, 1992, "Manufacturing Mechatronics Using Thermal Spray Shape Deposition," *Solid Freeform Fabrication Symposium*, pp. 272-279.
- Calvert, P., H. Denham, and T. Anderson, 1999, "Freeform Fabrication of Composites with Embedded Sensors," *Proceedings of SPIE-The International Society for Optical Engineering*, Vol. 3670, pp. 128-133.
- Cham, J. G., B. L. Pruitt, M. R. Cutkosky, M. Binnard, L. E. Weiss and G. Neplotnik, 1999, "Layered Manufacturing with Embedded Components: Process Planning Considerations," *Proceedings of 1999 ASME Design Engineering Technical Conference*, September 12-15.
- Cham, J. G., S. A. Bailey, J. E. Clark, R. J. Full and M. R. Cutkosky, 2002, "Fast and Robust: Hexapedal Robots via Shape Deposition Manufacturing," *The International Journal of Robotics Research*, 21, 10-11: 869-882.
- Danforth, S.C. and A. Safari, "Solid Freeform Fabrication: Novel Manufacturing Opportunities for Electronic Ceramics," IEEE International Symposium on Applications of Ferroelectrics, v.1, 1996, pp.183-188.
- Denham, H., G. George, L. Rintoul and P. Calvert, 1996, "Fabrication of Polymers and Composites Containing Embedded Sensors," *Proceedings of SPIE -The International Society for Optical Engineering*, v.2779, pp.742-747.
- Denham, H.B., T. A. Anderson, E. Madenci and P.D. Calvert, 1997, "Embedded PVF2 Sensors for Smart Composites," *Proceedings of SPIE - The International Society for Optical Engineering*, v.3040, pp.138-147.
- Finger, S., J. Stivoric, C. Amon, L. Gursoz, F. Prinz, D. Siewiorek, A. Smailagic and L. Weiss, 1996, "Reflections on a Concurrent Design Methodology: A Case Study in Wearable Computer Design," *Computer-Aided Design*, 28 (5) pp. 393-404.
- Geving, B., 1999, "Build Around a Screwdriver Shaft," <<http://rpm.marc.gatech.edu/~bgeving/experiments/screwdriver.html>>.
- Geving, B., and I. Ebert-Uphoff, 2000, "Enhancement of Stereo-Lithography Technology to Support Building Around Inserts," *Proceedings of the 2000 ASME Mechanisms and Robotics Conference*, Baltimore MD, September 10-13.
- Golnas, A., 1999, "Thin-Film Thermo-Mechanical Sensors Embedded in Metallic Structures," Doctoral Dissertation, Stanford University.
- Hatanaka, M. and R. Mark, 2003, "Process Planning for Embedding Flexible Materials in Multi-Material Prototypes," *Proceedings of the ASME Design Engineering Technical Conference*, vol. 3, pp. 325-333.
- Hatanaka, M., 2005, "Design and Fabrication of Multimaterial Flexible Mechanisms With Embedded Components," Doctoral Dissertation, Stanford University.
- Janaki Ram, G.D., C. Robinson, Y. Yang, and B. E. Stucker, 2007, "Use of Ultrasonic Consolidation for Fabrication of Multi-Material Structures," *Rapid Prototyping Journal*, 13 (4) pp. 226-235.
- Kataria, A., 2000, "Standardization and Process Planning for Building Around Inserts in Stereolithography Apparatus," Masters Thesis, Georgia Institute of Technology.
- Kataria, A., and D. W. Rosen, 2001, "Building Around Inserts: Methods for Fabricating Complex Devices in Stereolithography," *Rapid Prototyping Journal*, 7 (5), pp. 253-261.
- Kathryn, J. and F.F. Kong, 2002, "Procedure for Rapid Fabrication of Non-assembly Mechanisms with Embedded Components," *Proceedings of the ASME Design Engineering Technical Conference*, Montreal, Canada, September 29-October 2, pp. 1239-1245.
- Kong, C. Y. and R. Soar, 2005, "Method for embedding optical fibers in an aluminum matrix by ultrasonic consolidation," *Applied Optics*, 44, 6325-6333.
- Kong, C.Y., R. C. Soar and P.M. Dickens, 2004, "Ultrasonic Consolidation for Embedding SMA Fibres Within Aluminum Matrices," *Composite Structures*, 66 (1-4), pp.421-427.
- Kumar, V., S. Rajagopalan, M. Cutkosky and D. Dutta, 1998, "Representation and Processing of Heterogeneous Objects for Solid Freeform Fabrication," *Geometric Modeling Workshop*, Dec. 7-9, Tokyo.
- Li, X., 2001, "Embedded Sensors in Layered Manufacturing," Doctoral Dissertation, Stanford University.
- Li, X., 2003, "Embedded Fiber Bragg Grating Sensors in Polymer Structures Fabricated by Layered Manufacturing," *Journal of Manufacturing Processes*, 5(1), pp.78-86.
- Li, X., 2003, "Metal Embedded Fiber Bragg Grating Sensors in Layered Manufacturing," *Journal of Manufacturing Science and Engineering*, 125(3), pp. 577-586.

- Li, X., A. Glonas and F. Prinz, 2000, "Shape Deposition Manufacturing of Smart Metallic Structures with Embedded Sensors," *SPIE's 7th International Symposium on Smart Structures and Materials*, Vol. 3986, p.160-171.
- Liao, Y.S., H. C. Li and M. T. Chen, 2006, "The Study of Rapid Prototyping Process with Embedded Functional Inserts," *Journal of Materials Processing Technology*, Volumes 192-193, pp.68-74.
- Lopes, A.J., A. V. Inamdar, F. Medina, R. E. Hennessey, J. A. Palmer, B. D. Chavez, D.W Davis, P. G. Gallegos and R. B. Wicker, 2005, "Rapid Electromechanical Device Manufacturing using a Hybrid Direct Write Stereolithography System," *TexMEMS VII International Conference on Micro Electro Mechanical Systems*, Sept. 21-23, El Paso, TX.
- Medina, F., A. J. Lopes, A. V. Inamdar, R. Hennessey, J. Palmer, B. Chavez, D. Davis, P. Gallegos, and R.B. Wicker, 2005, "Hybrid manufacturing: Integrating direct write and stereolithography," *The Sixteenth Solid Freeform Fabrication Proceedings*, Austin, TX.
- Nau, W. H., 1991, "Embedding Sensors Using Stereolithography," Master of Science Thesis, Clemson University.
- Palmer, J. A., 2005, "Realizing 3-D Interconnected Direct Write Electronics Within Smart Stereolithography Structures," *ASME International Mechanical Engineering Congress and Exposition*, November 5-11, pp. 287-293, Orlando, FL.
- Robinson, C.J., B. Stucker, A. J. Lopes, R. Wicker, and J.A. Palmer, 2006, "Integration of Direct Write (DW) and Ultrasonic Consolidation (UC) Technologies to Create Advanced Structures with Embedded Electrical Circuitry," *Solid Freeform Fabrication Symposium*, Austin, TX.
- Safari, A. and S.C. Danforth, 1998, "Development of Novel Piezoelectric Ceramics and Composites for Sensors and Actuators by Solid Freeform Fabrication," *IEEE International Symposium on Applications of Ferroelectrics*, p.229-234.
- Siggard, E.J., A. S. Madhusoodanan, B. Stucker and B. Eames, 2006, "Structurally Embedded Electrical Systems Using Ultrasonic Consolidation (UC)", *Proceedings of the 17th Solid Freeform Fabrication Symposium*, Austin, TX.
- Siggard, E., 2007, "Investigative Research Into the Structural Embedding of Electrical and Mechanical Systems Using Ultrasonic Consolidation (UC)," Masters Thesis, Utah State University.
- Smailagic, A. and D. P. Siewiorek, 1993, "A Case Study in Embedded-System Design: The VuMan 2 Wearable Computer," *IEEE Design and Test of Computers*, 10 (3) pp. 56-67, September.
- Sun, L. and L.L. Shaw, 1999, "Solid Freeform Fabrication of In-situ SiC/C Thermocouples in Macrocomponents, " *Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science*, 30 (9), pp. 2549-2552.
- Sun, L., K. J. Jakubenas, J. E. Crocker, S. Harrison, L. L. Shaw and H.L. Marcus, 1998, "In Situ Thermocouples In Macro-components Fabricated Using SALD and SALDVI Techniques. II. Evaluation of processing parameters", *Materials and Manufacturing Processes*, 13 (6) pp.883-907.
- Weiss, L.E. and F.B. Prinz, 1997, "Shape deposition Manufacturing of Heterogeneous Structures," *Journal of Manufacturing Systems*, 16 (4) pp. 239-248.
- Yang, Y., 2008, "Fabrication of Long-Fiber-Reinforced Metal Matrix Composites Using Ultrasonic Consolidation," Doctoral Dissertation, Utah State University.